

# TEST 101 serial number: 60

### cotton soiled with carbon black/olive oil

(STANDARD REFERENCE MATERIAL FOR TECHNICAL TESTS ONLY)

#### generally:

according:	Swissatest standard soiling
suitable:	sensitive to the amount of detergent and to the level of agitation
date of production:	March 2023
durability:	December 2025 (reviewed in December 2024)
storing conditions:	must be well packed and kept in the fridge by < 8°C.

### specification of base material:

article 211	cotton fabric, percale, bleached, without optical brightener
thread count in cm	warp: 41
	weft: 65
yarn count in Nm	warp: 100
	weft: 100
weight in g/m <sup>2</sup>	90.0
width in cm	152.0
Y-value	88.9
Rem <sub>460nm</sub>	86.8

## specification of soiled fabric:

soiling	mixture of olive oil and soot olive oil, virgin olive oil soot, carbon pigment as descriped in IEC 60456
weight in g/m <sup>2</sup>	93.0
width in cm	143.4
Y-value	16.2
Rem <sub>460nm</sub>	15.6

measuring conditions:

instrument DC800V (spectrophotometer)

 $\begin{array}{ll} \text{illuminant / observer} & \text{D65 / } 10^{\circ} \\ \text{measuring geometry} & \text{d/8}^{\circ} \end{array}$ 

wavelength range 420 to 750nm filter UV barrier at 420nm

measuring diameter 26 mm gloss excluded