

TEST 167 serial number: 24

cotton, soiled with tea

generally:

| | |
|----------------------------|--|
| according: | Swissatest enzyme- and bleach monitors |
| suitable: | sensitive to bleaching agents and as a result of the temperature and the amount of heavy duty washing powder |
| date of production: | July 2022 |
| durability: | February 2038 |
| storing conditions: | must be well packed and kept in a fridge by < 8°C |

specification of base material:

| | |
|----------------------------------|---|
| article 221 | cotton fabric, cretonne, bleached, without optical brightener |
| thread count in cm | warp: 34 weft: 20 |
| yarn count in Tex | warp: 30 weft: 50 |
| weight in g/m² | 200.0 |
| width in cm | 167.0 |
| Y-value | 89.2 |
| Rem_{460nm} | 87.2 |

specification of soiled fabric:

| | |
|----------------------------------|--|
| soiling | soiled with black tea tea: black tea (Ceylon) |
| weight in g/m² | 207.0 |
| width in cm | 36.0 |
| Y-value | 40.7 |
| Rem_{460nm} | 24.7 |

measuring conditions:

| | |
|-----------------------|----------------------------|
| instrument | DC800V (spectrophotometer) |
| illuminant / observer | D65 / 10° |
| measuring geometry | d/8° |
| wavelength range | 420 to 750nm |
| filter | UV barrier at 420nm |
| measuring diameter | 26 mm |
| gloss | excluded |